

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.**

PRODUCTION OF BARIUM TITANATE POWDER

Patent number: JP6345432
Publication date: 1994-12-20
Inventor: KAWAMOTO MITSUTOSHI; others: 01
Applicant: MURATA MFG CO LTD
Classification:
- international: C01G23/00
- european:
Application number: JP19930131812 19930602
Priority number(s):

Abstract of JP6345432

PURPOSE: To obtain barium titanate high in dielectric constant and low in the dielectric loss and the temperature factor of dielectric constant by hydrolyzing a solution containing both titanium alkoxide and manganese alkoxide followed by hydrothermal reaction with a barium salt.

CONSTITUTION: The objective barium titanate can be obtained by hydrolyzing a solution containing both titanium alkoxide and manganese alkoxide with an alkali followed by hydrothermal reaction with a barium salt. The number of carbon atoms in the alkoxyl in said two kinds of alkoxide is pref. ≤ 15 (esp. ≤ 8). The barium titanate powder obtained above can be baked at relatively low temperatures, being small in grain size and capable of producing laminated capacitors low in voltage dependency.

Data supplied from the **esp@cenet** database - Patent Abstracts of Japan